

TECHNICAL SPECIFICATIONS

Manufacturing process	Needlefelt		ISO 2424
Surface aspect	Flat		ISO 2424
Fibre composition	70% Polyamide (PA) / 30% Polypropylene (PP)		
Backing	LV		ISO 2424
Width	200 cm, 400 cm		
Total fibre weight of use surface	600 g/m ²		
Total weight	1010 g/m ²	± 15%	ISO 8543
Total height	4,8 mm	+15% / -10%	ISO 1765
Flammability	Bfl-s1 (glued)		EN 13501-1
Overall use class	Class 33 - commercial heavy		EN ISO 10874
Luxury class	LC1		EN 1307
Castor chair suitability	Yes, permanent use		ISO 4918
Stair suitability	Yes, permanent use		EN 1307
Colour fastness to light	≥ 5		ISO 105-B02
Colour fastness to rubbing, wet and dry	≥ 4		ISO 105-X12
Colour fastness to water	≥ 4		ISO 105-E01
Colour fastness to soiling	≥ 3		EN 1269
Electrostatic charging	< 2 kV		ISO 6356
Impact sound protection ΔLW	20 dB		ISO 10140
Acoustical sound absorption	125 Hz 250 Hz 500 Hz 1000 Hz 2000 Hz 4000 Hz 0.03 α _s 0.06 α _s 0.09 α _s 0.17 α _s 0.26 α _s 0.42 α _s		ISO 354
Thermal resistance	0.09 m ² K/W (0.9 TOG)		ISO 8302
Slip resistance	DS (> 0,30)		EN 13893
GUT PRODIS-ID	4ADBEEF2		www.pro-dis.info

