

TECHNICAL SPECIFICATIONS

Manufacturing process	Needlefelt		ISO 2424
Type of surface	Flecked		
Surface aspect	Coarse fibred		ISO 2424
Fibre composition	100% Polyamide (PA)		
Backing	LV		ISO 2424
Width	200 cm		
Total fibre weight of use surface	540 g/m ²		
Total weight	1300 g/m ²	± 15%	ISO 8543
Total height	5,7 mm	+15% / -10%	ISO 1765
Flammability	Bfl-s1		EN 13501-1
Overall use class	Class 33 - commercial heavy		EN ISO 10874
Castor chair suitability	Yes, permanent use		ISO 4918
Stair suitability	Yes, permanent use		EN 1307
Colour fastness to light	> 7		ISO 105-B02
Electrostatic charging	< 2 kV		ISO 6356
Impact sound protection ΔLW	20 dB		ISO 10140
Acoustical sound absorption	125 Hz 250 Hz 500 Hz 1000 Hz 2000 Hz 4000 Hz 0,05 αs 0,05 αs 0,10 αs 0,18 αs 0,42 αs 0,69 αs		ISO 354
Thermal resistance	0,10 m ² K/W (1 TOG)		ISO 8302
Slip resistance	DS (> 0,30)		EN 13893

